



UNE - EN 13813

CEMHER

CEMHER®

- O R I G I N -

microterrazzo®

PRODUCT DESCRIPTION

One-component decorative coating consisting of the highest quality cements, fine fillers (<0.8 mm), additives, catalysts, inorganic coloring agents and synthetic resins.

After mixing it forms a continuous seamless coating with thickness from 4 mm, with high mechanical strength, without shrinking and retraction, and strong adhesion to any substrate: concrete, mortars, cement-containing

materials, etc.

It has the consistency of a white powder which, mixed with water, results in a ready to apply product of thick consistency. Despite the fact that the mortar is not self-leveling, the product is easily distributed with a trowel.

Classified according to UNE-EN 13813 as CT-C40-F10

PROPERTIES

- Continuous decorative pavement of multiple chromatic options.
- Applicable in thicknesses of 4 mm.
- High hardness and tenacity.
- Excellent adherence on multiple mineral substrates.
- Fast start-up.
- Can be protected with varnishes.
- No cracking.
- Shrinkage-compensating.

SUBSTRATE

Cement screeds. Concrete slabs with a resistance >15 MPa.

Non-porous substrates, troweled concrete, ceramics (prior treatment recommended).

CONSUMPTION

Microdur Base - 2 coats (2 x 1 kg/m²)
Microterrazzo - 2 coats (2 x 1,5 kg/m²)

APPLICATION

Mix 20 kg of Microterrazzo with 5 L of water (25%). Previously add the pigment concentrate to the water. The mixture should be blend with a mixer for at least 2 minutes, until a homogeneous mixture without lumps is obtained.

If you want to improve the fluidity to make easier the application, you can add a little more water, up to 6 L (30%), avoiding an excess that may impair the properties of the product.

The mixture can be used for 60 - 90 min at temperatures between +18° and +25 C°. Lower temperatures lengthen these times

and higher temperatures reduce them.

After mixing, the mixture should be poured in small quantities directly onto the substrate and then spread with a levelling trowel in a thin layer. It can also be applied standing in a thin layer using a squeegee trowel with a telescopic handle. Subsequently, a flexible trowel can be used to smooth and design the surface.

When several coats are applied, the next coat should be applied after 60 minutes and a maximum of 24 hours.



UNE - EN 13813

CEMHER

SEALING


After 24h, and prior to sealing, proceed to a surface sanding to remove impurities and smooth the surface.

Then apply two coats of pore-sealer Hydro-primer CI with a drying time of 4 hours after each coat.

After that apply 2 coats of solvent-based polyurethane varnish "Maxipur" or water-based varnish "Aquamax" with a drying time of 8 h between coats. It is very important to respect the drying times of the sealers.

TECHNICAL CHARACTERISTICS

Mixing ratio:	5 [25%] – 6 [30%] L water: 20 kg powder
Aparent density:	approx. 1,2 kg / L
Wet density:	approx. 2 kg / L
Consumption:	approx. 1,5 kg of powder/m ² ·mm
Minimum application temperature:	+ 10 °C
Workability (at 20°C):	approx. 60 - 90 minutes
Compressive strength:	1 day approx. 19 N/mm ² 7 days approx. 28 N/mm ² 28 days approx. 44 N/mm ²
Flexural strength:	1 day approx. 4,0 N/mm ² 7 days approx. 6,0 N/mm ² 28 days approx. 11,0 N/mm ²
Glanulometry:	max. 0,8 mm
Furniture with wheels:	yes
Suitable for water underfloor heating systems/ electric radiant floor heating systems:	yes / no
Ph range:	after 1 day: 12 pH
Packaging:	20 kg net buckets
Storage:	approx. 1 year in dry places and in its original closed container



CENTRAL OFFICE AND FACTORY

C/ Llanterners 44, 961 50 50 24
Pol. Ind. La Figuera info@cemher.com
46970 Alaquas
Valencia (ESPAÑA)

www.cemher.com